

## PRODUCT DATA



### CENTURION STONE SPECIFICATIONS

CENTURION PRODUCTS INC.  
50 VAN BUREN STREET  
NASHVILLE, TN 37208  
PHONE: 1-800-786-6352  
FAX: 615-726-1795

[WWW.CENTURIONSTONE.COM](http://WWW.CENTURIONSTONE.COM)

THIS SPECIFICATION GUIDE IS INTENDED TO BE USED IN THE PREPARATION OF SPECIFICATION FOR A PARTICULAR PROJECT OR AS THE BASIS OF AN OFFICEMASTER SPECIFICATION. IN EITHER CASE IT SHOULD BE EDITED TO MEET ACTUAL CONDITIONS AND NEEDS. LOCAL BUILDING CODES IN THE AREA OF CONSTRUCTION MAY REQUIRE ALTERING THE SPECIFICATIONS TO THEIR CODES.

THIS SPECIFICATION IS WRITTEN TO COVER CENTURION STONE MANUFACTURED STONE VENEER AND ACCESSORY TRIM ITEMS.

#### **PART 1.1 – GENERAL:**

- A. SECTION INCLUDES: PORTLAND CEMENT BASED MANUFACTURED STONE VENEER AND ACCESSORY TRIM ITEMS.
- B. **RELATED SECTIONS:**
  - 1. SUBSTRATE WALL FRAMING AND SHEATHING
  - 2. FLASHING & PERIMETER SEALING AT OPENING AND WALL PROTRUSIONS.
  - 3. MASONRY INSTALLATION ITEMS.
  - 4. METAL LATH & FASTENERS

**SPECIFIC NOTE:** REFER TO CENTURION STONES INSTALLATION MANUAL AND FLASHING INSTRUCTION SHEETS. ADD OR DELETE AS REQUIRED FOR SPECIFIC PROJECT.

#### **1.2 SUBMITTALS:**

- A. **PRODUCT DATA:** FOR EACH TYPE OF PRODUCT INDICATED.

#### **MANUFACTURER'S LITERATURE:**

- A-1. MATERIALS DESCRIPTION AND INSTALLATION INSTRUCTIONS.

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

- A-2. CERTIFIED TEST REPORTS ON PSI, ABSORPTION, SHEAR BOND, FLEX AND R&K INSULATION FACTORS IF REQUIRED.
- A-3. SAMPLES TO INCLUDE: ACTUAL SCALE PIECES OF VENEER UNITS SHOWING SIZE RANGE AND COLOR SELECTION AND TEXTURES OF PIECES TO BE USED.  
(MINIMUM SAMPLE SIZE 3FT. X 3FT.)
- A-4. SHOP DRAWINGS SHOWING INSTALLATION OF PRODUCT.
- A-5. MANUFACTURER'S INSTALLATION INSTRUCTIONS
- A-6. QUALIFICATION: PROOF OF MANUFACTURER'S QUALIFICATIONS, YEARS IN MANUFACTURING, LENGTH OF WARRANTIES, EVALUATION REPORTS ON PRODUCTS MINIMUM OF 3 YEARS MANUFACTURING EXPERIENCE IN MANUFACTURED STONE VENEER PRODUCTION.
- A-7. MAINTENANCE INSTRUCTIONS/SPECIAL WARRANTIES
- A-8. OBTAIN ARCHITECTS APPROVAL ON SAMPLE

### 1.3 QUALITY ASSURANCE:

- A. INSTALLER QUALIFICATIONS: A QUALIFIED INSTALLER WHO EMPLOYS EXPERIENCED STONEMASONS AND STONE FITTERS WITH MANUFACTURED STONE VENEER EXPERIENCE. MINIMUM OF 1 YEAR EXPERIENCE IN MANUFACTURED STONE VENEER INSTALLATION.

### 1.4 REFERENCES:

- A. BUILDING CODE APPLICABLE TO PROJECT SITE.
- B. (ANSI) AMERICAN NATIONAL STANDARDS INSTITUTE
  - 1. ANSIA 118.4 SPECIFICATIONS FOR LATEX-PORTLAND CEMENT MORTAR.
- C. (ASTM) AMERICAN SOCIETY FOR TESTING AND MATERIALS.
  - 1. ASTM C144 SPECIFICATION FOR AGGREGATE FOR MASONRY MORTAR.
  - 2. ASTM C207 SPECIFICATION FOR HYDRATED LIME FOR MASONRY PURPOSES.
  - 3. ASTM C39 TESTING FOR COMPRESSIVE STRENGTH
  - 4. ASTM C248 FLEXURAL STRENGTH
  - 5. ASTM C847 SPECIFICATION FOR METAL LATH

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

6. ASTM C226 SPECIFICATION FOR ASPHALT-SATURATED ORGANIC FELT.
7. ASTM 979 SPECIFICATIONS FOR PIGMENTS FOR INTEGRALLY COLORED CONCRETE.
8. ASTM C91 & C150 STANDARD FOR PORTLAND & MASONRY CONCRETE
9. ASTM C482 BEND STRENGTH

**D. UNIFORM BUILDING CODE (UBC)**

1. UBC STANDARD NO 15-5 FOR WATER ABSORPTION
2. UBC STANDARD NO 14-1 KRAFT WATERPROOF BUILDING PAPER.

**1.5 DELIVERY STORAGE AND HANDLING**

- A. STORE CEMENTITIOUS MATERIALS ON ELEVATED PLATFORMS, UNDER COVER AND IN A DRY LOCATION. AVOID EXPOSURE TO MOISTURE.
- B. STORE AGGREGATES SO THEY CAN BE MAINTAINED AND CONTAMINATION AVOIDED.
- C. STORE MASONRY ACCESSORIES INCLUDING METAL ITEMS, TO PREVENT CORROSION AND ACCUMULATION OF DIRT AND OIL.
- D. ORDERING COMPLY WITH MANUFACTURES ORDERING INSTRUCTIONS AND LEAD TIME REQUIREMENTS TO AVOID CONSTRUCTION DELAYS.
- E. DELIVERY: DELIVER MATERIALS IN MANUFACTURER'S ORIGINAL, UNDAMAGED CONTAINERS WITH IDENTIFICATION LABELS IN TACT.
- F. FOLLOW MANUFACTURER'S RECOMMENDATIONS ON HANDLING AND UNLOADING OF TRUCKS AND STONE STORAGE.
- G. THE CONTRACTOR SHALL CHECK THE MATERIALS UPON DELIVERY TO SITE TO ASSURE THAT PROPER MATERIAL HAS BEEN RECEIVED.
- H. THE CONTRACTOR SHALL PREVENT EXCESSIVE MUD, WET CEMENT, AND LIKE MATERIAL, WHICH MAY AFFIX THEM, FROM COMING IN CONTACT WITH THE MATERIAL.

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

#### 1.6 ENVIRONMENTAL REQUIREMENTS:

- A. CONSULT LOCAL BUILDING CODES FOR COLD WEATHER CONSTRUCTION REQUIREMENTS WHEN AIR TEMPERATURE IS 40 DEGREES F OR BELOW (AC1530.1/ASCE6/TMS602)
- B. PROTECT MATERIAL FROM RAIN, MOISTURE AND FREEZING TEMPERATURES, PRIOR TO AND FOR 48 HOURS AFTER COMPLETION OF WORK.
- C. CONSULT LOCAL BUILDING CODES FOR HOT WEATHER CONSTRUCTION REQUIREMENTS STONE MATERIALS AND WALL SURFACE MAY BE DAMPEN TO REDUCE WALL TEMPERATURE BEFORE APPLYING STONE VENEER. (ACT 530.1/ASCE6/TMS602)
- D. ALLOW NO CONSTRUCTION ACTIVITY ON OPPOSITE SIDE OF WALL DURING INSTALLATION AND FOR 48 HOURS AFTER COMPLETION OF WORK.
- E. PROTECT SURFACES OF WINDOWS AND DOOR FRAMES AND SIMILAR PRODUCTS WITH PAINTED AND INTEGRAL FINISHES, FROM MORTAR DROPPINGS.
- F. TURN SCAFFOLD BOARDS NEAR THE WALL ON EDGE AT END OF EACH DAY TO PREVENT RAIN FROM SPLASHING MORTAR AND DIRT ON COMPLETED STONE MASONRY.

#### 1.7 WARRANTY

- A. MANUFACTURER'S WARRANTY: SUBMIT FOR OWNERS ACCEPTANCE MANUFACTURER'S WARRANTY NOTE: CENTURION STONE PRODUCTS ARE COVERED UNDER A 50 YEAR WARRANTY FROM DATE OF PURCHASE WHEN INSTALLED IN ACCORDANCE WITH MANUFACTURES INSTRUCTIONS.
- B. PROJECT REQUIREMENT WARRANTIES: REFER TO PROJECT WARRANTY PROVISIONS AND CONDITIONS OF CONTRACT AND SPECITY TERMS.

#### 1.8 COORDINATION

- A. ADVISE INSTALLERS OF OTHER WORK SPECIFIC REQUIREMENTS FOR PLACEMENT OF FLASHING AND SIMILAR ITEMS TO BE BUILT INTO STONE MASONRY.

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

#### PART 2 **PRODUCTS**

- 2.1**
- A. CENTURION STONE PRODUCTS TEL: 615-256-6694  
50 VAN BUREN STREET FAX: 615-726-1795  
NASHVILLE, TN 37208 WWW.CENTURIONSTONE.COM
- B. (                    VENEER) VENEER TYPES AS SHOWN ON  
DRAWING
- C. **SUBSTITUTIONS:** NO SUBSTITUTIONS PERMITTED
1. PRODUCTS CLAIMING TO BE THE SAME AS OR EQUAL  
SHOULD MEET OR EXCEED THE FOLLOWING  
SPECIFICATIONS

#### **2.2** **MANUFACTURED STONE VENEER**

CENTURION STONE VENEERS ARE USED INTERIOR AND EXTERIOR ON BOTH RESIDENTIAL AND COMMERCIAL PROJECTS. THE VENEER CAN BE APPLIED ON METAL OR WOOD FRAMING AS WELL AS OVER MASONRY WALLS. CENTURION STONE VENEER IS CAST IN MOLDS MADE FROM NATURAL STONE BY MASTER MOLD CRAFTSMAN WHO SELECT CHOICE PIECES FOR THEIR SIZE SHAPE AND TEXTURES.

- A. **VENEER UNITS:** CENTURION STONE IS MANUFACTURED USING A UNIQUE PROCESS OF CASTING A MIX DESIGN OF ALL NATURAL MATERIALS CONSISTING OF PORTLAND CEMENTS, SAND, LIGHTWEIGHT AGGREGATES AND IRON OXIDE COLORS, INTO MOLDS THAT PRODUCT THE LOOK AND FEEL OF NATURAL STONE. THE AVERAGE THICKNESS OF THE 22 PATTERNS RANGE FROM 1 ½” TO 3” DEPENDING ON PATTERN WITH THE FOLLOWING MIX DESIGN RESULTS
- B. **PHYSICAL PROPERTIES:**
1. COMPRESSIVE STRENGTH: 7849 PSI
  2. SHEAR BOND (ADHESION STRENGTH): 160
  3. WATER ABSORPTION: 11%
  4. FREEZE-THAW TEST: .13
  5. THERMAL RESISTANCE: R-.44 – K4.D33
  6. DENSITY: 93 PCF
  7. SHIPPING WEIGHTS: 7 ½ TO 12 LBS SQ FT

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

- C. **PACKAGING:** PACKAGING TO BE IN CORRAGATED PACKAGING WITH SET AMOUNTS IN EACH PACKAGE (BOX) CENTURION PACKAGING IS ONE OF THE BEST IN THE INDUSTRY WITH 8 INDIVIDUAL BOXES ON A WOOD PALLET WITH A WATER RESISTANT WRAPPER AROUND THE 8 BOXES. THE PACKAGE CAN BE MOVED EASILY WITH A TOW MOTOR AND THEN BY INDIVIDUAL BOXES ON THE JOB SITE. SPECIFIER NOTE: IF SUBSTITUTIONS ARE PERMITTED THEY SHOULD MEET OR EXCEED THE ABOVE REQUIREMENTS AND SUBMIT THE TEST RESULTS ON THEIR PRODUCTS.
- D. **MOISTURE BARRIER:** ASTM D226 NO 15 NON PERFORMED ASPHALT SATURATED FELT. UBC STANDARD NO 14-1 KRAFT WATERPROOF BUILDING PAPER.
- E. **METAL LATH/REINFORCING:** (ASTM C847 GALVANIZED EXPANDED METAL LATH) (ASTM C847 PAINTED EXPANDED METAL LATH) (1 INCH GALVANIZED STEEL, 18 GAUGE WOVEN WIRE MESH COMPLYING WITH CODE AGENCY REQUIREMENTS)

### 2.3

#### **MORTAR:**

1. PORTLAND CEMENT: ASTM C150 TYPE I OR MASONRY CEMENT TYPE S, ASTM C270
2. SAND: ASTM C144 NATURAL OR MANUFACTURED SAND
3. LIME: ASTM C207, TYPE S
4. PIGMENT: ASTM C979 MINERAL OXIDE PIGMENTS (USE ONLY PIGMENTS WITH A RECORD OF SATISFACTORY PERFORMANCE IN STONE MASONRY MORTAR)
5. LATEX ADDITIVE: ACRYLIC-RESIN PR STYRENEBUTADIENE RUBBER WATER EMULSION SERVING AS REPLACEMENT FOR PART OR ALL OF GAGING WATER (WHEN INSTALLING DRY STACK SERIES OF STONE)
6. COLD WEATHER ADMIXTURE: NONCHLORIDE, NONCORROSIVE, ACCELERATING ADMIXTURE WITH ASTM C494/C494M, TYPE C.
7. LOADER: PORTABLE
8. SEALER: IF REQUIRED (NOT NECESSARY WITH CENTURION STONE) WATER BASED SILANE OR SILOXANE MASONRY SEALER (CLEAR) SEMI-GLOSS) FINISH

## PRODUCT DATA



### MANUFACTURER'S INSTALLATION INSTRUCTIONS

#### 2.4

##### FLASHING

- A. METAL FLASHING: PROVIDE METAL FLASHING COMPLYING WITH (SMACNA'S ARCHITECTURAL SHEET METAL MANUAL) (DIVISION 7 SECTION SHEET METAL FLASHING AND TRIM)
- B. TAPES/RUBBER FLASHING (BY GRACO)

#### PART 3

##### EXECUTION:

#### 3.1

##### EXAMINATION

- A. VERIFICATION OF SITE CONDITIONS: EXAMINE SURFACES INDICATED TO RECEIVE STONE VENEER WITH INSTALLER PRESENT, FOR COMPLIANCE WITH REQUIREMENTS FOR INSTALLATION TOLERANCE AND OTHER CONDITIONS AFFECTING PERFORMANCE.
- B. EXAMINE SUBSTRATE TO VERIFY THAT WALL FRAMING, SHEATHING, FLASHING AND WEATHER RESISTANT SHEATHING PAPER IS INSTALLED CORRECTLY AND INSTALLATION WILL RESULT IN A WEATHERPROOF COVERING.
- C. NOTIFY CONTRACTOR IN WRITING OF CONDITIONS DETREMENTAL TO THE PROPER AND TIMELY COMPLETION OF THE WORK. DO NOT PROCEED WITH THE WORK UNTIL UNSATISFACTORY CONDITIONS HAVE BEEN CORRECTED.

#### 3.2

##### PREPARATION

- A. PROTECTION: PROTECT ADJACENT WORK FROM CONTACT WITH MORTAR
- B. SURFACE PREPARATION: PREPARE SUBSTRATE IN ACCORDANCE WITH MANUFACTURER'S INSTRUCTIONS FOR THE TYPE OF SUBSTRATE BEING COVERED
- C. CONCRETE AND MASONRY SURFACES, NEW, CLEAN UNTREATED SURFACES: NO PREPARATION IS NECESSARY. IF RELEASING AGENT IS PRESENT USE HIGH PRESSURE WATER WASH OR ETCH SURFACE WITH MURIATIC ACID AND RINSE THOROUGHLY
- D. CLEAN DIRTY OR STAINED STONE SURFACE BY REMOVING SOIL STAINS AND FOREIGN MATERIALS BEFORE SETTING. USE ONLY MILD CLEANING COMPOUNDS THAT CONTAIN NO CAUSTIC OR HARSH MATERIALS OR ABRASIVES.





**MANUFACTURER'S INSTALLATION INSTRUCTIONS**

**3.3 INSTALLATION**

**NOTE:** WHEN APPLYING STONE IN HOT OR DRY WEATHER THE WALL AND BACK OF EACH PIECE SHOULD BE MOISTENED WITH A FINE SPRAY OF WATER TO PREVEN EXCESSIVE OBSORPTION OF MOISTURE FROM THE MORTAR. APPLICATIONS SHOULD BE PROTECTED FROM FREEZING SINCE FROZEN MORTAR WILL NOT SET UP PROPERLY UNDER FREEZING CONDITIONS.

**A. SETTING OF STONE VENEER**

PERFORM NECESSARY FIELD CUTTING AND TRIMMING AS STONE IS SET, USE POWER SAWS TO FIELD CUT STONES.

1. SORT STONE BEFORE THEY ARE SET FOR SIZE, WIDTH, AND HEIGHTS, COLORS RELATING TO AESTHETIC EFFECTS, DISCARD UNSUITABLE PIECES.
2. WORK OUT OF SEVERAL BOXES TO ENSURE COLOR VARIATIONS IS UNIFORMLY BLENDED THROUGH OUT JOB
3. ALTERNATE LONG AND SHORT OF CORNER PIECES
4. MAINTAIN UNIFORM MORTAR JOINTS IN GROUPED PATTERNS 1/2" TO 3/4" IN WIDTH. WHENINSTALLING THE DRY STACK SERIES OF STONE PATTERNS THE STONE IS SET TIGHT AGAINST EACH OTHER WITH NO MORTAR JOINT ALLOWED

**B. MORTAR JOINTS**

1. GROUT ALL JOINTS UNIFORMALY FILL WITH GROUTING BAG. ALLOW GROUT TO SET UP TO CRUMBLY CONSISTENCY. RAKE AND BRUSH JOINTS TO A SMOOTH AND CONSISTANT FINISH ACCEPTABLE TO ARCHITECT.
2. EXCESS MORTAR: CLEAN EXCESSIVE MORTAR FROM STONES FACE AS WORK PROCEEDS. DO NOT ALLOW MORTAR TO SET UP ON FACE OF UNITS. CLEAN AND FINISH JOINTS PER MANUFACTURER'S INSTRUCTIONS





**CENTURION STONE SPECIFICATIONS**

**3.4 ADJUSTING AND CLEANING**  
**ADJUSTING**

- A. DAMAGED UNITS SHOULD BE REPLACED WITH NEW UNITS DURING CONSTRUCTION
- B. BROKEN CHIPPED STAINED OR OTHERWISE DMAGED STONE MAY BE REPAIRED IF METHODS AND RESULTS ARE APPROVED BY ARCHITECT.
- C. REMOVE AND REPLACE DEFECTIVE JOINTS
- D. REPLACE STONE IN A MANNER THAT RESULTS IN STONE MASONRY MATCHING APPROVED SAMPLES AND MOCKUPS.

**CLEANING**

- A. REFERENCE SECTION 0174D-CLEANING
- B. REMOVE ANY PROTECTIVE COVERING FROM ADJACENT WORK
- C. IF CLEANING IS REQUIRED CLEAN WORK WITH A SOLUTION OF GRANULATED HOUSEHOLD DETERGENT AND WATER SOLUTION USING SOFT BRISTLE BRUSH. RINSE WITH CLEAN WATER. ALLOW 24 HOURS FOR WORK TO SET UP BEFORE CLEANING
- D. DO NOT USE A WIRE BRUSH FOR CLEANING. DO NOT CLEAN USING ACID OR ACID BASED PRODUCTS. DO NOT CLEAN WITH HIGH PRESSURED WASHER. DO NOT USE DE-ICING CHEMICALS IN AREAS NEXT TO VENEER
- E. SCUFFING: SCUFFING MAY OCCUR IN SHIPPING OR HANDLING OF STONE VENEER. SCUFFING OCCURS IN NATURAL STONE AND SOME MAY OCCUR IN MANUFACTURED STONE VENEER MOST SCUFF MARKS CAN BE ELIMINATED BY THE ABOVE CLEANING PROCESS.
- F. EFFORESCENCE: CLEAN AREA WITH WATER AND STIFF BRISTLE BRUSH, AND RINSE. ON DIFFICULT AREAS CLEAN BY USING 1 PART HOUSEHOLD VINEGAR TO 5 PARTS WATER. RINSE THOROUGHLY.

**3.5 EXCESS MATERIALS AND WASTE**

- A. EXCESS STONE: STACK EXCESS STONE WHERE DIRECTED BY OWNER
- B. EXCESS MASONRY WASTE: REMOVE FROM JOB SITE WASTE THAT CANNOT BE USED AS FILL AND LEGALLY DISPOSED OF OFF OWNER'S PROPERTY

